

MOTIP Metallic Paint

Ord.-no.: look at ordering information

Technical Information



Fast-drying acrylic paint for treated and untreated surfaces including wood, metal, aluminium, stone and various types of plastic. It offers excellent adhesion and is resistant to scratches and the weather. For best results, first apply a base layer of MOTIP White Primer.

Quality & properties

- Fast drying
- Wear resistant
- Resistant to weather influences
- Excellent coverage

Physical & chemical data

- Base: Nitrocombi resin
- Colourname:
 - ◊ green
 - ◊ blue
 - ◊ red
 - ◊ silver
 - ◊ gold
 - ◊ brown
 - ◊ black
 - ◊ violet
- Degree of gloss: gloss, >75 GU
- Efficiency: 400 ML – 1.25 - 1.75 m²
- Dry to touch: 10 - 20 min
- Dust dry: 5 - 10 min
- Completely dry: 120 min
- Overcoatable: 120 min
- Surfaces: Wood, metal, glass, stone and various types of plastic.
- Minimum Working Temperature: 10 °C
- Maximum Working Temperature: 25 °C
- Vapour pressure: 8300/20 bar
- Temperature Resistance: – 110 °C
- Storage stability: 10 y
- Content: 400 ML

How to use

- Before use, carefully read the directions on the packaging and act accordingly.
- Pre Treatment: The surface should be clean, dry and free of grease. Remove loose old lacquer and rust and sand the surface. In order to achieve the best metallic effect, apply a layer of white MOTIP primer. When treating surfaces of plastic, first apply a layer of plastic primer before applying the MOTIP white primer. After drying, sand the base layer (grain 600).
- Treatment: The surface should be clean, dry and free of grease. The aerosol should have room temperature. Best processing temperature 10 to 25°C.
- Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 centimetre.
- Apply the lacquer in several thin layers. Before applying the next layer, again shake the aerosol.
- After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).
- The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.
- Recommendation: The metallic effect is increased by using a first layer of MOTIP Wheel Spray Silver and by applying a finishing layer of MOTIP acrylic clear varnish.

performance. The caps and packagings are made of recyclable material.

Disposal

Only the completely emptied cans should be put into the recycling skip or appropriate container for reclaimable refuse. Cans which are not empty should be disposed off as "special refuse".

Marking/Labelling

All products made by European Aerosols comply with the actual labelling regulations according to Preparation Guideline 1999/45/EG. All aerosols correspond to TRGS 200 and TRG 300 as well as to aerosol guideline 75/324/EWG in the actually valid version.

For any further technical questions call our hotline +31 (0) 561 69 44 00 from Monday to Thursday from 9 h a.m. to 3 h p.m. or on Friday until 12 h p.m.

As of August 17, 2022 – This release replaces all eventually earlier issued versions.

European Aerosols GmbH, Kurt-Vogelsang-Straße 6, 74855 Haßmersheim - info-de@european-aerosols.com

European Aerosols B.V., Wolfraamweg 2, NL-8471 XC Wolvega - info-nl@european-aerosols.com